

## THE STRUCTURES OF TWO NOVEL Sn<sup>2+</sup> OXYSALTS FOUND WITH ROMARCHITE AND HYDROROMARCHITE AS CORROSION PRODUCTS OF PEWTER ARTIFACTS

ANDREW J. LOCOCK<sup>§</sup>, ROBERT A. RAMIK AND MALCOLM E. BACK

*Mineralogy, Department of Natural History, Royal Ontario Museum,  
100 Queen's Park, Toronto, Ontario, Canada M5S 2C6*

### ABSTRACT

The crystal structures of an anthropogenic Sn<sup>2+</sup> silicate,  $\text{Sn}_6\text{O}_4(\text{SiO}_4)$ , hexagonal, space group  $P6_3mc$ ,  $a$  7.3742(4),  $c$  11.9598(10) Å,  $V$  563.23(6) Å<sup>3</sup>,  $Z$  = 2,  $D_{\text{calc}}$  5.12 g/cm<sup>3</sup>, and an anthropogenic Sn<sup>2+</sup> sulfate,  $\text{Sn}_6\text{O}_4(\text{SO}_4)(\text{OH})_2$ , orthorhombic, space group  $Pbca$ ,  $a$  14.0071(8),  $b$  12.5016(7),  $c$  14.5030(9) Å,  $V$  2539.6(3) Å<sup>3</sup>,  $Z$  = 8,  $D_{\text{calc}}$  4.74 g/cm<sup>3</sup>, were refined by full-matrix least-squares techniques on the basis of  $F^2$  to agreement indices  $R1$  (Sn<sup>2+</sup> silicate and Sn<sup>2+</sup> sulfate) of 3.0 and 4.2%, calculated for 704 and 3281 unique observed reflections ( $|F_o| \geq 4\sigma_F$ ), and  $wR_2$  of 5.5 and 11.0% for all data, respectively. Intensity data were collected at room temperature using MoK $\alpha$  radiation and a CCD-based area detector. Both structures contain the [Sn<sub>6</sub>φ<sub>8</sub>] cluster [φ: O<sup>2-</sup> or (OH)<sup>-</sup>], which has been found in several stannous compounds, and which can be derived from the structure of fluorite. These two compounds occur with romarchite, SnO, and hydroromarchite,  $\text{Sn}_3\text{O}_2(\text{OH})_2$ , on pewter bowls that had become corroded in cold freshwater for approximately 160 years.

**Keywords:** romarchite, hydroromarchite, stannous compounds, tin compounds, corrosion, pewter, non-merohedral twin, silicate, sulfate, fluorite derivative, crystal structure.

### SOMMAIRE

Nous avons affiné la structure cristalline d'un silicate de Sn<sup>2+</sup> anthropogénique,  $\text{Sn}_6\text{O}_4(\text{SiO}_4)$ , hexagonal, groupe d'espace  $P6_3mc$ ,  $a$  7.3742(4),  $c$  11.9598(10) Å,  $V$  563.23(6) Å<sup>3</sup>,  $Z$  = 2,  $D_{\text{calc}}$  5.12 g/cm<sup>3</sup>, et un sulfate de Sn<sup>2+</sup> anthropogénique,  $\text{Sn}_6\text{O}_4(\text{SO}_4)(\text{OH})_2$ , orthorhombique, groupe d'espace  $Pbca$ ,  $a$  14.0071(8),  $b$  12.5016(7),  $c$  14.5030(9) Å,  $V$  2539.6(3) Å<sup>3</sup>,  $Z$  = 8,  $D_{\text{calc}}$  4.74 g/cm<sup>3</sup>, par techniques de moindres carrés sur matrice entière en utilisant les facteurs  $F^2$ , jusqu'à un résidu  $R1$  (silicate et sulfate) de 3.0 et 4.2% calculé pour 704 et 3281 réflexions uniques observées ( $|F_o| \geq 4\sigma_F$ ), et une valeur de  $wR_2$  égale à 5.5 et 11.0% pour toutes les données, respectivement. Les données d'intensité ont été prélevées à température ambiante avec rayonnement MoK $\alpha$  et un détecteur à aire de type CCD. Les deux structures contiennent des groupes [Sn<sub>6</sub>φ<sub>8</sub>], φ correspondant à O<sup>2-</sup> ou (OH)<sup>-</sup>, dérivés de la structure de la fluorite, tout comme dans plusieurs composés d'étain bivalent. On trouve ces deux composés associés à la romarchite, SnO, et la hydroromarchite,  $\text{Sn}_3\text{O}_2(\text{OH})_2$ , sur des bols en alliage d'étain devenus corrodés suite à leur submersion dans l'eau fraîche froide pour environ 160 ans.

(Traduit par la Rédaction)

**Mots-clés:** romarchite, hydroromarchite, composés stanneux, composés d'étain, corrosion, alliage d'étain, macle non méroédrique, silicate, sulfate, dérivé de fluorite, structure cristalline.

---

<sup>§</sup> Current address: Department of Earth and Atmospheric Sciences, University of Alberta, 1-26 Earth Sciences Building, Edmonton, Alberta, Canada T6G 2E3. E-mail address: alocock@ualberta.ca